

KURO

KRAFT



TECHNICAL DATA SHEET

GRADE:
GRAMMAGE

KURO KRAFT BROWN
158 gr/m²

PROPERTY	UNIT	TARGET VALUE	TEST METHOD
Grammage *	gr/m ²	158 ± 5	UNI-ISO 536
Ash content	%	10 ± 1	UNI-ISO 1762
Porosity (gurley)	s/100 ml	14 ± 2	UNI-ISO 5636-5
Wet strenght **	N/15mm	>7	UNI 10398
pH water extract	pH	8,0 ± 0,5	UNI-ISO 6588-1
Density	kg/m ³	600 ± 50	UNI-ISO 534

* at 4% moisture

**N/m according point 9.2 UNI10398

** At the production

All values according vith Giacosa lab. measurement
T23°C/50% RH

Sede : 10070 FRONT C.SE (TO) Via Rivera, 2

Tel. +39(011) 92.50.111 | FAX +39(011) 92.51.681

e - mail info@cartieragiacosait

cartiera
giacosa
www.cartieragiacosait

KURO

KRAFT



TECHNICAL DATA SHEET

GRADE:
GRAMMAGE

KURO KRAFT BROWN
170 gr/m²

PROPERTY	UNIT	TARGET VALUE	TEST METHOD
Grammage *	gr/m ²	170 ± 5	UNI-ISO 536
Ash content	%	10 ± 1	UNI-ISO 1762
Porosity (gurley)	s/100 ml	15 ± 2	UNI-ISO 5636-5
Wet strenght **	N/15mm	>7	UNI 10398
pH water extract	pH	8,0 ± 0,5	UNI-ISO 6588-1
Density	kg/m ³	600 ± 50	UNI-ISO 534

* at 4% moisture

**N/m according point 9.2 UNI10398

** At the production

All values according vith Giacosa lab. measurement
T23°C/50% RH

Sede : 10070 FRONT C.SE (TO) Via Rivera, 2

Tel. +39(011) 92.50.111 | FAX +39(011) 92.51.681

e - mail info@cartieragiacosait

cartiera
giacosa
www.cartieragiacosait

KURO

KRAFT



TECHNICAL DATA SHEET

GRADE:
GRAMMAGE

KURO KRAFT BROWN
190 gr/m²

PROPERTY	UNIT	TARGET VALUE	TEST METHOD
Grammage *	gr/m ²	190 ± 5	UNI-ISO 536
Ash content	%	10 ± 1	UNI-ISO 1762
Porosity (gurley)	s/100 ml	15 ± 2	UNI-ISO 5636-5
Wet strenght **	N/15mm	>7	UNI 10398
pH water extract	pH	8,0 ± 0,5	UNI-ISO 6588-1
Density	kg/m ³	600 ± 50	UNI-ISO 534

* at 4% moisture

**N/m according point 9.2 UNI10398

** At the production

All values according vith Giacosa lab. measurement
T23°C/50% RH

Sede : 10070 FRONT C.SE (TO) Via Rivera, 2

Tel. +39(011) 92.50.111 | FAX +39(011) 92.51.681

e - mail info@cartieragiacosait

cartiera
giacosa
www.cartieragiacosait

KURO

KRAFT



TECHNICAL DATA SHEET

GRADE:
GRAMMAGE

KURO KRAFT BROWN
213 gr/m²

PROPERTY	UNIT	TARGET VALUE	TEST METHOD
Grammage *	gr/m ²	213 ± 7	UNI-ISO 536
Ash content	%	10 ± 1	UNI-ISO 1762
Porosity (gurley)	s/100 ml	15 ± 2	UNI-ISO 5636-5
Wet strenght **	N/15mm	>7	UNI 10398
pH water extract	pH	8,0 ± 0,5	UNI-ISO 6588-1
Density	kg/m ³	600 ± 50	UNI-ISO 534

* at 4% moisture

**N/m according point 9.2 UNI10398

** At the production

All values according vith Giacosa lab. measurement
T23°C/50% RH

Sede : 10070 FRONT C.SE (TO) Via Rivera, 2

Tel. +39(011) 92.50.111 | FAX +39(011) 92.51.681

e - mail info@cartieragiacosait

cartiera
giacosa
www.cartieragiacosait